

FLEXTUBE DRY CEMENT HOSE

Dry Cement Discharge Hose N2496

APPLICATION AND KEY POINTS:

- For discharge of dry powdered cement or powdered lime from bulk pneumatic trailers
- Static conductive tube

TEMPERATURE RANGE:

• -20°F to +180°F

BURST PRESSURE:

Minimum 4:1

MATERIAL TUBE:

- ½ smooth, seamless extruded styrene-butadiene (SBR)
- Abrasion-resistant
- Static conductive

MATERIAL COVER:

- Black styrene-butadiene (SBR)
- Excellent abrasion, weather, and ozone resistance

BRANDING:

- Green longitudinal mylar stripe: GOODALL® N2496
 FLEXITUBE DRY CEMENT 100 PSI MAX W.P. MADE IN
 CANADA 10001 REFER TO INDUSTRY
 RECOMMENDATIONS FOR PROPER CARE &
 MAINTENANCE
- Embossed stripe: MFR C-Y-M

STANDARD LENGTHS:

100 feet

REINFORCEMENTS:

• Single high-tensile textile braid

TECHNICAL SPECIFICATIONS				
ID (in)	OD (in)	Max WP (psi)	Min BR (in)	Weight (lb/ft)
4	4.44	100	7	1.29
All data at 68° F				

LAYLINE: GOODALL N2496 FLEXITUBE DRY CEMENT

All information contained on this datasheet is subject to change without prior notice. GOODALL MAKES NO WARRANTIES. EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE. Buyer/end-user is responsible for determining whether the Goodall product is fit for a particular purpose and suitable for buyer/s/user's method of use or application. Failure to follow procedures for selection, installation, care, maintenance, and storage of hoses may result in the hose's failure to perform properly and may result in damage to property and/or serious injury. Goodall or any of its affiliates or subsidiaries shall not be subject to and disclaims any obligations or liabilities (including but not limited to all consequential, incidental, and contingent damages) arising from tort claims (including without limitation negligence and strict liability) or other theories of law.